

RECEPOX COATING TX

Product description

RECEPOX COATING TX is a two-component epoxy resin used as a pigmented topcoat. The product is available in any color. The coating has a glossy finish and low is low maintenance. It is a coating material for use in interior building floor constructions.

Application

RECEPOX COATING TX can be used in a variety of flooring systems for a wide range of applications:

- Top-coat for RECEPOX products
- Roller application
- Suitable for layered broadcasted systems
- The mixture has thixotropic properties
- Finely textured surface
- Workability is optimized for lower ambient temperatures

Product benefits

- Shortened workability enables application at lower temperatures compared to standard epoxy materials
- High mechanical resistance
- High chemical resistance
- Increased UV resistance
- High overcoating ability
- Easy application
- Good adhesion to most materials
- Optimal processing time/workability
- Low maintenance surface

Material properties

Bulk density: ~1 600 kg/m³

Dry matter content by weight: ~ 100%

Dry matter content by volume: ~ 100%

Hardness D-Shore: 72

Flexural strength: 45,4 MPa

(ČSN EN ISO 178)

Tensile adhesion: > 1,5 N/mm²

(ČSN 74 4505)

Consumption: 0,15-0,3 kg/m²

Workability *: 28 min.

HDT after 7 days: 37,8 °C (ČSN EN ISO 75-1)

HDT after 30 days: 40,9 °C (ČSN EN ISO 75-1)

Curing time: minimum 24 hours

Dynamic viscosity (AB)**: 2900 mPa.s

Application conditions:

Ambient air temperature: 10-25 °C

Substrate temperature: 10-25 °C

Substrate moisture content: < 4%


Ambient relative humidity: < 60 %

* 200 g sample

** Anton Paar method, spindle 6, T = 22 °C



Roller application



Thickness
0,2 mm



Consumption
0,15-0,30
kg/m²



VOC
FREE



Solvent
FREE



Glossy
surface



Thixotropic



Fast system

Packaging

RECEPOX COATING TX is supplied in pre-measured containers containing component A (resin) and component B (hardener).

Component A [kg]	29,68
Component B [kg]	6,32
Component A+B [kg]	36,00

The supplied packaging of components A and B ensures the correct mixing ratio for both components. Do not split the components; the units are designed to be mixed completely.

Material properties

All technical data in the product's technical data sheet are based on laboratory tests. Values may vary depending on ambient conditions, which are beyond our control.

Heat resistance

Load*	Dry heat
Permanent	+ 50 °C
Short-time max. 7 days	+ 80 °C
Short-time max. 12 hours	+ 100 °C

*without simultaneous chemical and mechanical loading

Color


RECEPOX COATING TX is available in desired color after curing. The colors of the individual components may slightly vary individually. Component A is a pigmented liquid. Component B is a transparent yellowish fluid.

Storage conditions

Store components A and B in a dry place at temperatures between 15 °C and 30 °C. Protect from direct sunlight, excessive heat, and frost. When stored in unopened original containers, the product has a shelf life of 2 years from the date of manufacture stated on the label.



Roller application



Thickness
0,2 mm



Consumption
0,15-0,30
kg/m²



VOC
FREE



Solvent
FREE



Glossy
surface



Thixotropic



Fast system

Chemical resistance


Acetic acid 45%	not resistant	MIP SMX	long-term resistant
Hydrogen peroxide 27%	long-term resistant *	SAVO Original	long-term resistant*
Formic acid 7,5%	short-term resistant*	Amoniac 15%	long-term resistant
Nitric acid 40%	short-term resistant*	MIP ALU	resistant
Phosphoric acid 55%	long-term resistant*	Aquanta OXI	resistant*
Hydrofluoric acid 18%	long-term resistant*	KMnO₄ 10%	long-term resistant*
Acetone	not resistant	AgNO₃ 10%	long-term resistant*
Ethanol 98%	long-term resistant	Horolith N	long-term resistant
Hydrochloric acid 27%	long-term resistant	Chloran	long-term resistant
Sodium hydroxide 50%	long-term resistant	Topaz AC 5	long-term resistant
Citric acid conc.	long-term resistant	Lactic acid 5%	resistant
Sulfuric acid 20%	long-term resistant	Tartaric acid conc.	long-term resistant

If you need to know the chemical resistance of RECEPOX COATING TX to any not-listed chemical, please consult technical support.

**A colour change might occur*



Roller application



Thickness 0,2 mm



Consumption 0,15-0,30 kg/m²



VOC FREE



Solvent FREE



Glossy surface



Thixotropic



Fast system

Substrate preparation

The material should be applied to a surface free of most impurities, such as dust, grease, paint, waxes etc. In case of a dirty or damp substrate, prior priming using RECEPOX PRIMER WO or RECEPOX PRIMER WO TX is highly recommended.

Mixing

RECEPOX COATING TX is supplied in appropriate quantities of component A and component B. These two components are to be mixed in their entirety. If it is necessary to mix a smaller quantity, component A is mixed with component B in a ratio of 4,7:1. In this case Recetex waives any responsibility for potential defects in the material. Mixing must be carried out mechanically, using a high-performance slow-speed drill/mixer with a suitable mixing attachment. Mixing must be carried out at a speed of 400-600 rpm for a minimum of 2 minutes.

Application


The material must be applied at 15-25 °C, with an ambient relative humidity of maximum 60 % on a pre-treated surface. The material must be applied as soon as possible after mixing. After a longer period of time, due to the large volume of the material, a rapid increase in viscosity and temperature occurs, which makes it impossible to pour and process the material. Adapt the workflow to the actual conditions at the application site. RECEPOX COATING TX must cure for at least 24 hours before the next layer is applied, however, longer curing time may reduce the adhesion of the next layer. After 7 days the material is fully cured and able to carry the full load.

Recommendation

Apply only in a dry environment at recommended application conditions. Avoid direct skin contact and do not inhale fumes/mist/aerosol/etc. When working with RECEPOX COATING TX always use personal protection equipment specified on the manufacturing label or in the safety data sheet. Avoid leakage of the material into the environment and handle packaging in accordance with environmental regulations.



Roller application



Thickness
0,2 mm



Consumption
0,15-0,30
kg/m²



VOC
FREE



Solvent
FREE



Glossy
surface



Thixotropic



Fast system

Notes


- If you have any questions about resistance to a specific chemical, please contact technical support via www.recetex.com
- The safety data sheet is available on request via www.recetex.com
- Technical support is available for telephone consultation regarding specific customer requirements, including telephone application support.

LEGAL ANNEX

Information and, for the most part, recommendations on the application and use of Recetex products by end users are provided in good faith based on Recetex's existing knowledge and experience with these products, assuming proper storage, handling and use under normal conditions in accordance with Recetex's recommendations. In practice, no warranty of merchantability or fitness for any particular purpose or any liability arising from any legal relationship can be inferred from this information or from any written advice or other advice given, given the differences in materials, background and actual conditions on the ground. The user of the product must test beforehand whether the product is suitable for the intended use and purpose. Recetex reserves the right to change the characteristics of its products. The property rights of third parties must be respected. All orders are accepted in accordance with the Terms and Conditions of Sale and Delivery as amended. Users are always obliged to consult the latest version of the product data sheet for the product in question, a copy of which will be sent on request.



Roller application



Thickness
0,2 mm



Consumption
0,15-0,30
kg/m²



VOC
FREE



Solvent
FREE



Glossy
surface



Thixotropic



Fast system